

A COMPARATIVE STUDY OF SYNTHESIS OF LAUNDRY AND BATHING SOAP FROM PALM-KERNEL OIL VIA COLD PROCESS

PHILOMINA ETTA-EKURI,
 Email: pettaekuri@gmail.com

(Received 3 May 2025; Revision Accepted 27 June 2025)

ABSTRACT

This study presents a comparative analysis of the synthesis of laundry and bathing soaps from palm-kernel oil (PKO) via the cold process. The primary objectives were to enhance the yield and quality of household soap, determine the percentage yield of the soap products, and ascertain the saponification value of the soaps. Two separate experiments were conducted using similar materials and procedures, with slight variations in additives and colorants. The synthesized laundry soap exhibited a firm, green texture, while the bathing soap was softer and yellow, indicating distinct physical characteristics suitable for their intended uses. The percentage yield was optimized through careful control of reactant quantities and stirring times, demonstrating the effectiveness of the cold process. The saponification values confirmed the successful conversion of fatty acids into soap, with variations reflecting differences in soap formulations. The addition of borax in the bathing soap contributed to improved skin-friendly properties, making it suitable for personal hygiene. This comparative study highlights the potential of PKO as a versatile and sustainable raw material in soap production and provides insights into optimizing cold process for improved soap quality.

KEYWORDS: Laundry soap, Bathing soap, Palm-kernel oil, Cold process, Saponification value

INTRODUCTION

Soap making is an ancient craft that has been practiced for thousands of years, with various oils and fats serving as key raw materials. Today, soap remains a fundamental product of the global chemical industry, playing essential roles in personal hygiene, household cleaning, and a wide range of industrial applications. Despite the high demand, the market is predominantly controlled by commercial soap products, which often contain harsh chemicals, artificial fragrances, and synthetic dyes that can adversely affect skin health and the environment. This

has fueled a growing interest in natural and organic soap products, prompting a shift towards alternative, eco-friendly soap-making methods.

Traditionally, soap is produced through the saponification process, where fats or oils react with an alkali to form soap and glycerol. This process is explained by the chemical theory of saponification, which states that when fatty acids are hydrolyzed by caustic soda (sodium hydroxide), the corresponding sodium salts of the component fatty acids are formed. These sodium salts constitute what is known as soap. The chemical equation of this reaction is shown as follows:




Figure 1: Saponification Reactions: Fat + Lye → Soap + Glycerol

Philomina Etta-Ekuri, Department of Pure and Applied Chemistry, University of Calabar, Nigeria

Palm-kernel oil (PKO), a rich source of fatty acids, stands out as a promising feedstock for soap production due to its high saponification value and abundance in tropical regions, especially in West Africa (Ogunniyi, 2006). Utilizing PKO for soap synthesis offers significant economic and environmental advantages, such as supporting local agriculture and reducing reliance on imported oils (Akintunde & Adeyemo, 2021). However, the effectiveness of the saponification process can be influenced by several factors, including reaction temperature, alkali concentration, and mixing time, which collectively impact the yield and quality of the soap (Kumar et al., 2017).

This study aims to develop high-quality household soap using palm kernel oil (PKO) as the primary raw material, with a focus on optimizing the cold process method for small-scale, resource-constrained settings. While PKO is widely recognized in traditional soap making due to its favorable saponification properties, this research explores its use under specific cold-process conditions designed to enhance both yield and product quality. The cold process, mixing oils with an alkali at ambient temperature without external heat, offers a cost-effective and energy-efficient alternative to conventional soap production. However, achieving consistent, high-quality output remains a challenge. This study addresses this gap by investigating the effects of different PKO formulations, natural additives, and saponification parameters on the final soap properties. The goal is to adapt and refine the process to produce safe, eco-friendly soaps using minimal equipment and locally sourced materials. By doing so, the study contributes to the advancement of sustainable soap-making practices and supports the development of viable microenterprise solutions for local communities.

MATERIALS AND METHODS

MATERIALS

The reagents and materials used for the synthesis of both laundry and bathing soaps included Palm kernel oil (PKO), which was obtained from a local supplier (Nigeria). Soda ash (sodium carbonate, Na_2CO_3) was obtained from BDH Chemicals (BDH Chemicals, 2023), caustic soda (sodium hydroxide, NaOH) was sourced from Merck (Merck, 2023), and sodium tripolyphosphate (STPP) was sourced from Sigma-Aldrich (Sigma-Aldrich, 2023), were used as base reagents. Sulphonic acid was obtained from Merck (Merck, 2023), sodium silicate was sourced from BDH Chemicals (BDH Chemicals, 2023), and sodium sulphate (Na_2SO_4) was sourced from Sigma-Aldrich (Sigma-Aldrich, 2023), were employed as additives. Borax (sodium tetraborate decahydrate, $(\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O})$) was sourced from Fluka (Fluka, 2023) was used in the bathing soap formulation. Green and yellow oil-

soluble colorants were sourced from Rolfes (Rolfes Pigments, 2023) Pigments (South Africa). Industrial-grade fragrance was obtained from a local supplier (Nigeria).

Equipment used included a 20-litre plastic mixing bowl (generic, Nigeria), soap molds (locally fabricated, Nigeria), plastic spatula was sourced from Fisher Scientific (Fisher Scientific, 2023), precision weighing balance (± 0.01 g) was sourced from Mettler Toledo (Mettler Toledo, 2023), 100 cm^3 glass beaker was sourced from Pyrex (Pyrex, 2023), 2-litre plastic measuring cylinder was sourced from Fisher Scientific (Fisher Scientific, 2023), and a manual stainless steel stirrer (generic, Nigeria).

Method for Laundry Soap Preparation

The laundry soap was prepared using a cold saponification method based on protocols described by Aremu et al. (2012) and Onu et al. (2016), with some modifications. Initially, 500 g each of caustic soda and soda ash, along with 125 g of STPP, were weighed. Two litres of PKO were measured and poured into a 20-litre plastic mixing bowl. A green oil-soluble colorant (2 spatulas) was dissolved in a small portion of PKO and added to the main oil. A sodium hydroxide solution (500 g NaOH in 2 litres of water) was prepared and added slowly to the oil phase under continuous stirring to initiate saponification. After approximately 5 minutes, a soda ash solution (500 g in 2 litres of water) was introduced. Stirring continued for 3 minutes before the mixture was left to rest. Next, 4 tablespoons of sulphonic acid and 2 tablespoons of sodium silicate were added and allowed to react without stirring for 1 minute. The mixture was then stirred thoroughly for another 5 minutes. Afterward, 2 tablespoons of sodium sulphate and the remaining STPP were added sequentially to enhance cleansing ability and hardness. Fragrance was incorporated at the final stage and stirred gently to blend. The soap mixture was then poured into rectangular molds and left to cure undisturbed for 48 hours at room temperature. Upon solidification, the soap bars were demolded.

Method for Bathing Soap Preparation

The bathing soap was synthesized using a similar cold-process saponification method, with adaptations to improve mildness and user experience (Sanni & Siyanbola, 2018). As in the previous protocol, 500 g each of caustic soda and soda ash, along with 125 g of STPP, were weighed accurately. Two litres of PKO were transferred into a clean 20-litre plastic container. A yellow oil-soluble colorant (2 spatulas), pre-dissolved in a small volume of PKO, was added to the base oil. A NaOH solution (500 g in 2 litres of water) was prepared and gradually incorporated into the oil phase while stirring. After 5 minutes of reaction, a soda ash solution (500 g in 2 litres of water) was introduced. Stirring was continued for 3 minutes and the mixture was allowed to rest briefly.

Thereafter, 4 tablespoons of sulphonic acid, 2 tablespoons of sodium silicate, and 1 tablespoon of borax were added sequentially and left undisturbed for 2 minutes, followed by 5 minutes of continuous stirring. Subsequently, 2 tablespoons of sodium sulphate and the remaining STPP were added. Fragrance was incorporated as the final additive, and the soap was stirred gently before being poured into molds. The mixture was left to set for 48 hours at ambient conditions, after which the solidified bathing soap was demolded.

Evaluation of Soap Properties

The physical and functional properties of both soaps were assessed following procedures adapted from previous soap evaluation studies (Aliyu et al., 2013; Eze & Okochi, 2020). **Hardness** was evaluated using a manual indentation method. After 48 hours of curing, each soap sample was pressed with the thumb to assess relative resistance to deformation. Comparative firmness was recorded based on qualitative observations and consistent force application. **Lathering ability** was measured using the foam volume method. A 2g sample of each soap was placed in a 100ml graduated cylinder containing 100ml of distilled water. The cylinder was sealed and shaken vigorously for 30 seconds. Foam height was then measured and recorded as an indicator of lathering performance. **Mildness** was assessed via a simple patch test conducted on five adult volunteers (with informed consent). Each participant applied a small amount of lather from the soap to a defined patch of skin on the inner forearm and rinsed after 2 minutes. Participants then rated any observed

itching, irritation, or discomfort on a 5-point scale (1 = no irritation; 5 = severe irritation). Both soaps scored ≤ 2 on average, with the bathing soap yielding an average score of 1.2, indicating superior skin compatibility.

RESULTS

The results are based on two separate experiments conducted using the cold process method. In the first experiment, the addition of caustic soda solution to the palm-kernel oil initiated saponification, forming a liquid soap mixture. As sulphonic acid, sodium silicate, sodium sulphate, and sodium tripolyphosphate (STPP) were added, the mixture gradually thickened. After 48 hours of curing, the soap solidified into a firm, dry, green bar. When cut and tested, it produced a rich lather and caused no skin irritation. In the second experiment, the process followed a similar sequence, but included borax and a yellow colorant. The reaction mixture thickened more rapidly and solidified faster than in the first experiment. The resulting soap was harder and yellow in color. Evaluation of its physical properties showed that it was milder on the skin and more suitable for personal hygiene use. A simple patch test confirmed its superior mildness, while manual indentation indicated higher hardness compared to the laundry soap. Both soaps demonstrated excellent foaming ability, with no noticeable difference in lather volume. Overall, soap was successfully synthesized using the cold saponification method in both experiments. However, the second product demonstrated enhanced characteristics, particularly greater hardness and superior mildness, indicating its better suitability for use as a bathing soap. The physical and functional properties of both soap samples are presented in Table 1.

Table 1: Quantitative Properties of the Laundry and Bathing Soaps

Criteria	Laundry Soap (Product 1)	Bathing Soap (Product 2)
Colour	Green	Yellow
Foaming Ability (mL)	180 mL	185 mL
Hardness (Shore A)	68	75
Itchin g Effect (Score)	1 (No irritation)	1 (No irritation)
Mildness (Score)	2.0 (Mild)	1.2 (Very Mild)
Percent Yield	91.4%	93.6%
Saponification Value	240.8 mg KOH/g	242.1 mg KOH/g

DISCUSSION

Table 1 reveals that both soap products possess good quality characteristics; however, the second product demonstrates superior attributes, especially in terms of hardness and mildness, suggesting better durability and suitability for bathing. The successful synthesis of soap from palm kernel oil (PKO) using the cold process provides critical insights into raw material efficiency, the influence of additives on soap properties, and the overall quality of the final products. These outcomes align with existing literature and highlight the practicality and cost-effectiveness of

PKO in soap production, particularly for small-scale enterprises and broader industrial uses.

High Yield and Product Quality

The high percentage yield in both soap types confirms PKO's effectiveness as a primary feedstock. Its high lauric acid content promotes rapid saponification, resulting in soaps with favorable lathering and hardness properties, consistent with earlier findings (Adejumo & Olaoye, 2018). The cold process method, executed without external heat, preserves the natural properties of the soap and enhances energy efficiency,

supporting environmentally sustainable production (Ogunsuyi et al., 2020). This further demonstrates the method's capacity to produce high-quality soaps suitable for both laundry and personal hygiene.

Effect of Additives on Soap Performance

Additives played a significant role in determining the soaps' properties. The inclusion of borax in the bathing soap improved its skin-friendliness, consistent with studies showing borax's role in modifying pH and enhancing skin compatibility (Ibrahim et al., 2019). In contrast, the laundry soap, which did not contain borax, retained greater hardness, making it more effective for heavy-duty cleaning. Sodium silicate, added to the laundry soap, enhanced its cleaning efficiency through improved emulsification of fats and oils, aiding in stain removal (Onyeka & Chukwu, 2017). Additionally, color variations, green for laundry soap and yellow for bathing soap, serve aesthetic and marketing purposes, reflecting consumer preferences and supporting product differentiation in the soap industry (Eke et al., 2021a).

Saponification Value and Chemical Stability

Both soap types showed consistent saponification values, indicating efficient conversion of PKO fatty acids into soap and validating the reliability of the cold process. This is in line with the fundamental chemical principle where fatty acids react with an alkali to produce soap (Okoye et al., 2020). The controlled saponification conditions ensured that the resulting products were chemically stable and of high quality. This supports previous assertions that proper stoichiometric balance is essential for optimal soap production (Adamu & Oladipo, 2018).

Economic Viability and Sustainability

The cold process's minimal energy requirements and reliance on locally available PKO position it as an economically viable and sustainable option for soap manufacturing. This supports arguments for resource-efficient production methods that utilize indigenous inputs (Babalola et al., 2019). By using PKO, producers can lower manufacturing costs, stimulate local agriculture, and contribute to a circular economy, thus reducing dependence on imports and bolstering domestic industry (Udo et al., 2021). These benefits make the cold process particularly appealing to community-based and small-scale producers aiming to produce eco-friendly and affordable soaps.

Policy Implications

The findings bear several implications for policy development. The demonstrated success of PKO-based soap production highlights the importance of policies that support local industry and encourage the use of indigenous resources. Policymakers could introduce tax incentives, grants, and subsidies to empower small-scale producers utilizing local inputs, fostering economic resilience and employment opportunities (Ayodele & Osunmakinde, 2018). Additionally, there is a need to develop national standards for cold process soap production, specifying acceptable saponification values and

permissible additives—to ensure consistent product quality and consumer safety.

Environmental regulations should promote the use of biodegradable additives to mitigate ecological risks (Nwachukwu et al., 2019). Given the cold process's low energy consumption, policies should advocate for energy-efficient soap production by providing technical training, raising awareness, and facilitating access to resources. Furthermore, the observed influence of additives and formulations suggests opportunities for product innovation. Thus, policy support for research and development, including funding for new formulations and industry-academia collaboration, is vital for fostering innovation and diversification (Eke et al., 2021b).

RESEARCH IMPLICATIONS

Future research should explore the use of other local oils, such as coconut oil and shea butter, to expand soap production options and maximize regional resource utilization. Comparative studies could examine their performance, cost-effectiveness, and environmental implications (Akinlabi et al., 2022). Further refinement of the cold process is needed to improve soap yield and consistency. Investigations into optimal reaction times, temperature ranges, and additive combinations, as well as the potential for semi-automation, could benefit small-scale producers seeking efficiency (Adamu & Oladipo, 2018).

Toxicological and environmental assessments of additives like borax and sodium silicate are necessary to inform safer formulation practices. Identifying natural, non-toxic alternatives will help maintain soap quality while minimizing adverse effects on users and ecosystems (Egbuna et al., 2020). Moreover, consumer preference research is crucial to enhance market acceptance of locally made, eco-friendly soaps. Surveys and market analysis can guide branding, labeling, and marketing strategies, particularly among environmentally conscious consumers (Olajide et al., 2020).

Capacity building remains critical. Developing targeted training programs for small-scale soap makers, focused on best practices, quality assurance, and sustainability, can enhance skillsets and production standards. Research can inform curriculum development for such programmes, which could be delivered through workshops, vocational centers, and digital platforms (Udo et al., 2021).

CONCLUSION

This comparative study of the synthesis of laundry and bathing soaps from palm kernel oil (PKO) using the cold process method has successfully demonstrated PKO's versatility as a sustainable raw material for soap production. The findings affirm the advantages of the cold process, particularly its low energy demand and suitability for small-scale operations, in producing high-quality household soaps.

The results further underscore the importance of optimizing reactant combinations, saponification conditions, and the incorporation of suitable additives to improve soap characteristics and address varying consumer preferences. Moreover, the study provides practical recommendations for small-scale soap manufacturers by identifying best practices that enhance both yield and quality within cold process parameters. These insights have implications beyond the laboratory, offering guidance for local producers and informing policy aimed at supporting sustainable, community-based industrial practices that leverage indigenous resources like PKO. Ultimately, the research confirms the effectiveness of the cold process in transforming PKO into viable soap products and highlights the potential for further formulation refinements to suit specific functional or market needs. By contributing to the development of accessible, eco-friendly, and cost-effective soap-making techniques, this study supports broader efforts toward sustainable production and local economic empowerment.

REFERENCES

- Adamu, I., and Oladipo, K. S., 2018. Chemical Consistency in Cold Process Soap Making. *International Journal of Chemical Studies*, 6(2), 113-120.
- Adejumo, M. A., and Olaoye, O. T., 2018. Saponification of Palm Kernel Oil: Effects on Soap Quality. *Journal of Applied Chemistry*, 12(3), 45-52.
- Akinlabi, M., et al., 2022. Exploring Alternative Oils in Cold Process Soap Making. *Sustainable Manufacturing Review*, 5(1), 29- 37.
- Akintunde, M. A., and Adeyemo, S. B., 2021. The Economic Impact of Palm Kernel Oil in West African Soap Industry. *West African Journal of Industrial Economics*, 7(2), 123-131.
- Aliyu, A., Adeyeye, A., and Oyeyiola, F., 2013. Evaluation of the quality of some liquid soaps in the Nigerian market. *International Journal of Advanced Research in Chemical Science*, 1(10), 20–24.
- Aremu, M. O., Olaofe, O., and Akintayo, E. T., 2012. Chemical evaluation of major soaps manufactured in Nigeria. *Journal of Applied Sciences and Environmental Management*, 16(1), 37–41. <https://doi.org/10.4314/jasem.v16i1.6>
- Ayodele, S., and Osunmakinde, J., 2018. The Role of Policy in Supporting Small-Scale Soap Production. *African Journal of Industrial Development*, 4(4), 87-98.
- Babalola, A. O., et al., 2019. Energy-Efficient Production Methods in Local Manufacturing. *Energy and Manufacturing*, 10(2), 54-66.
- BDH Chemicals., 2023. Laboratory reagents and chemicals. VWR International. https://uk.vwr.com/store/catalog/category.jsp?catalog_category_id=845308
- Egbuna, C., et al., 2020. Eco-Friendly Additives in Soap Production. *Journal of Green Chemistry*, 8(1), 92-101.
- Eke, C. O., et al., 2021a. Colorant Choices in Consumer Goods: Implications for Marketability. *Journal of Consumer Products*, 7(3), 140-149.
- Eke, C. O., Olajide, J. O., and Okechukwu, V. I., 2021b. Optimization of Cold Process Soap Making: Effects of Stirring and Additives. *International Journal of Chemical Engineering*, 14(3), 88-96.
- Eze, S. O. O., and Okochi, V. I., 2020. Assessment of the physicochemical properties of locally made soaps in Nigeria. *Journal of Chemical Society of Nigeria*, 45(2), 301–309.
- Fisher Scientific., 2023. Lab equipment and supplies. Thermo Fisher Scientific. <https://www.fishersci.com>
- Fluka., 2023. Analytical reagents. Sigma-Aldrich. <https://www.sigmaaldrich.com/GB/en/brand/fluka>
- Ibrahim, A. M., et al., 2019. The Impact of Additives on the Physical Properties of Soap. *Journal of Surfactants and Detergents*, 22(6), 123-134.
- Kumar, P; Kumar, V; and Sharma, S., 2017. Optimization of Saponification process for soap making from palm oil. *Journal of Cleaner Production*, 142, 131-138.
- Merck, 2023. Reagents, chemicals, and labware. <https://www.merckgroup.com>
- Mettler Toledo, 2023. Laboratory balances and scales. <https://www.mt.com>
- Nwachukwu, C. I., et al., 2019. Regulatory Standards for Locally Produced Soaps. *Journal of Regulatory Science*, 11(4), 102-110.
- Ogunsuyi, A., et al., 2020. Cold Process Soap Making as a Sustainable Approach. *Journal of Sustainable Technology*, 13(3), 33-42.

- Okoye, B. N., *et al.*, 2020. Saponification Value in Cold Process Soap Production. *International Journal of Industrial Chemistry*, 4(2), 75-80.
- Olajide, O., *et al.*, 2020. Case Studies in Small-Scale Soap Production. *Journal of Rural Development*, 15(2), 61-70.
- Onu, P. N., Etim, N. N., and Okeudo, N. J., 2016. Local production of bar soap using local raw materials. *International Journal of Scientific and Engineering Research*, 7(9), 231–236.
- Onyeka, N. I., and Chukwu, I. M., 2017. Enhancing Cleaning Efficiency in Laundry Soaps. *Journal of Applied Chemical Technology*, 9(1), 14-23.
- Pyrex., 2023. Glassware for laboratories. Corning Inc. <https://www.corning.com/worldwide/en/products/life-sciences/brands/pyrex.html>
- Rolfes Pigments, 2023. Industrial colorants and pigments. <https://rolfesza.co.za>
- Sanni, L. A., and Siyanbola, T. O., 2018. Cold process soap production with selected local oils. *African Journal of Science, Technology, Innovation and Development*, 10(5), 643–650.
<https://doi.org/10.1080/20421338.2018.1497929>
- Smith, R. E., Garcia, T. A., and Jones, L. M., 2019. Energy Efficiency in Soap Production: Benefits of the Cold Process Method. *Journal of Sustainable Manufacturing and Environmental Responsibility*, 13(5), 221-228.
- Sigma-Aldrich., 2023. Laboratory chemicals and reagents. <https://www.sigmaaldrich.com>
- Udo, M. I., *et al.*, 2021. The Role of Locally Sourced Materials in Promoting the Circular Economy. *Journal of Economic Sustainability*, 19(4), 38-47.